

IN THE CLAIMS

Please amend the claims as follows:

Claims 1-13 (Canceled).

Claim 14 (Currently Amended): A polyurethane composition comprising

(A) a urethane compound prepared by reacting 100 parts by weight of a polyol with a polyisocyanate such that the NCO/OH equivalent weight ratio is greater than 0.5 but less than 15, and

(B) ~~a dimer an oligomer formed of 2 to 8 molecules~~ of a linear olefin compound having 6 to 30 carbon atoms,

wherein the content of said compound (B) per 100 parts by weight of said polyol is greater than 5 parts by weight but less than 400 parts by weight.

Claim 15 (Currently Amended): The polyurethane composition of claim 14, wherein ~~the oligomer formed of 2 to 8 molecules~~ dimer ~~of a linear olefin compound having 6 to 30 carbon atoms for said compound (B) is an oligomer formed of 2 to 4 molecules~~ a dimer of a linear olefin compound having 10 to 15 carbon atoms.

Claim 16 (Currently Amended): The polyurethane composition of claim ~~14~~ 15, wherein the ~~dimer oligomer formed of 2 to 4 molecules of a linear olefin compound having 10 to 15 carbon atoms~~ is ~~any one of~~ 2-butyl-1-octene, 2-hexyl-1-decene, 2-octyl-1-dodecene, 2-decyl-1-tetradecane, 2-dodecyl-1-hexadecane, or 2-tetradecyl-1-octadecane, ~~a decene trimer, a decene tetramer, a dodecene trimer, a dodecene tetramer, a tetradecene trimer, and a tetradecene tetramer.~~

Claim 17 (Previously Presented): A molded article prepared by molding the polyurethane composition of claim 14.

Claim 18 (New): The polyurethane composition of claim 14, wherein the dimer is 2-butyl-1-octene.

Claim 19 (New): The polyurethane composition of claim 14, wherein the dimer is 2-hexyl-1-decene.

Claim 20 (New): The polyurethane composition of claim 14, wherein the dimer is 2-octyl-1-dodecene.

Claim 21 (New): The polyurethane composition of claim 14, wherein the dimer is 2-decyl-1-tetradecane.

Claim 22 (New): The polyurethane composition of claim 14, wherein the dimer is 2-dodecyl-1-hexadecane.

Claim 23 (New): The polyurethane composition of claim 14, wherein the dimer is 2-tetradecyl-1-octadecane.

Claim 24 (New): The polyurethane composition of claim 14, wherein the dimer is a dimer of 1-decene.

Claim 25 (New): The polyurethane composition of claim 14, wherein the dimer is a dimer of 1-hexene.

Claim 26 (New): The polyurethane composition of claim 14, wherein the content of said compound (B) per 100 parts by weight of said polyol is 10 to 200 parts by weight.

Claim 27 (New): The polyurethane composition of claim 14, wherein the content of said compound (B) per 100 parts by weight of said polyol is 40 to 150 parts by weight.

Claim 28 (New): The polyurethane composition of claim 14, wherein the NCO/OH equivalent weight ratio is greater than 0.5 but less than 2.

Claim 29 (New): The polyurethane composition of claim 14, wherein the NCO/OH equivalent weight ratio is 0.9 - 1.2.

Claim 30 (New): The polyurethane composition of claim 14, wherein the NCO/OH equivalent weight ratio is 2 - 10.

Claim 31 (New): The polyurethane composition of claim 14, wherein the NCO/OH equivalent weight ratio is 2 - 8.

Claim 32 (New): The polyurethane composition of claim 14, consisting essentially of said urethane compound and said dimer.

Claim 33 (New): The polyurethane composition of claim 14, said composition being free of phthalic ester plasticizer.

Claim 34 (New): The polyurethane composition of claim 27, wherein the NCO/OH equivalent weight ratio is 0.9 - 1.2.

Claim 35 (New): The polyurethane composition of claim 27, wherein the NCO/OH equivalent weight ratio is 2 - 8.